



MATFER

TECHNICAL SPECIFICATION

BAKEWELL code 111320

QUALITY: BAKEWELL – SILICONIZED BAKING PAPER

		Target	Min	Max	Typical Value
Grammage	gm ²	41.0	39.5	42.5	-
Release (tape test)	sec	2	-	10	-
Greaseproofness (HELGA)	ml/h	430	-	2210	-
Tensile MD	kN/m	-	-	-	4.2
Tensile CD	kN/m	-	-	-	2
Burst strength 245°C / 6 mins	kPa	105	85	-	-
ISO Brightness C/2	%	72	65	85	-
Moisture	%	-	-	-	5

- ◆ Allow foods (especially meringues) to cool down before lifting them off the Bakewell.
- ◆ Both sides of the Bakewell can be used.
- ◆ Maximum temperature 230°C.